

CHRYSO®CI 550

Corrosion Inhibitor

Chryso
Concrete
Solutions

17/10/2024



DESCRIPTION

CHRYSO®CI 550 is a liquid admixture for steel protection, to be added into concrete. It can also be used in repair mortars and grouts.

CHRYSO®CI 550 is composed of efficient corrosion inhibitors, combined with polyfunctional agents and a phosphonic combination made of amine salts, which increases corrosion inhibition properties.

CHRYSO®CI 550 protects steel by a well proven, migratory inhibition function.

A unique feature of **CHRYSO®CI 550** is that the inhibitor will migrate a considerable distance through concrete to provide protection and will stop further corrosion of reinforcing metals.

BENEFITS

- **CHRYSO®CI 550** increases life of all reinforced concrete structures.
- Effectively protects against corrosion. It even migrates into the densest of concrete and to adjoining areas to protect surrounding metal elements and provides efficient protection against carbonation and attack by atmospheric gasses such as CO_2 , SO_2 , chlorides and so on.
- **CHRYSO®CI 550** is water based, organic and non-flammable, therefore safe and user friendly. It does not contain any calcium nitrite.

PACKAGING

- 210 L drum
- IBC 1000L
- Bulk delivery on request

FIELDS OF APPLICATION

In fresh concrete mixes, **CHRYSO®CI 550** will seek out and form a corrosion inhibiting protective layer on metals. When used with cementitious repair mortars and grouts, **CHRYSO®CI 550** will migrate and reach undisturbed parent concrete, providing efficient corrosion protection to rebar's which are already in place.

- All cement types
- Precast elements
- Foundation concrete below water table
- Marine construction
- Concrete exposed to defrost salts
- Concrete in contact with water
- Concreting in aggressive environments
- etc

CHRYSO® CI 550

Corrosion Inhibitor

Chryso
Concrete
Solutions

17/10/2024

INDICATIVE INFORMATION

Product Nature	liquid
Color	Colourless to light yellow
Lifetime	18 months
Specific gravity	0,930 ± 0,020
pH	11,00 ± 2,00

Cl⁻ ion content: nil to EN 934 and BS 5075.

METHOD OF USE

- The optimum dosage of this product can only be established after trial tests, taking into account the rheological characteristics and the required mechanical performances of the concrete.
- It can be added: - either within mixing water, or at the end of the mixing cycle (extra mixing time) - or gradually: part in the water before mixing, part during the mixing cycle.
- Should the product be added to fresh concrete, into the mixing truck, it is necessary to mix at high speed, and then at low speed (with a minimum of 3 minutes, at each speed).
- At a high dosage, the product may generate a light set retarding effect on some cement.
- **CHRYSO® CI 550** is recommended to be used at a ratio of one litre per cubic meter of concrete. Moreover, dosage rate can vary depending on concrete quality, as per mix design.
- It can also be added at the same dosage rate into repair mortars and grouts.
- The concrete mix design should take into consideration the water available in **CHRYSO® CI 550**.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using outside recommended dosage ranges.

PRECAUTIONS

- Protect from frost.
- Use at a temperature above 0° C.
- Should the product freeze, it will recover its properties. After thawing, an efficient agitation is necessary until the product is entirely homogeneous again.

Compatibility:

- **CHRYSO® CI 550** is compatible with all types of Portland cement, class C and F fly ash, GGBS, microsilica, fibers and approved air entraining admixtures.
- **CHRYSO® CI 550** is compatible with other CHRYSO admixtures when used in the same concrete mix, but should be added to the mix separately and must not be mixed together prior to addition.

SAFETY

CHRYSO® CI 550 is not considered dangerous to handle.

Prior to any use, please read carefully the Material Safety Data Sheets.