

CHRYSO®Delta CQ 11

New Generation, high range water reducing/
superplasticizing admixture



DESCRIPTION

CHRYSO®Delta CQ 11 is a new generation superplasticizer based on modified polycarboxylate and synthetic polymers particularly recommended for readymix concrete and civil engineering construction sites.

Thanks to its specifically designed molecular structure, **CHRYSO®Delta CQ 11** enables the concrete manufacturer to produce cohesive, low viscous concrete with long workability retention.

CHRYSO®Delta CQ 11 intends to create a high water reduction and/or an increased period of workability retention. It allows the manufacture of concrete with a long workability retention without prejudicial set retarding effect. Thus, it can be used in a wider concrete range.

BENEFITS

- **CHRYSO®Delta CQ 11** allows concrete with the required workability to be obtained, while reducing the water/cement ratio.
- Enhances the workability retention of concrete in hot climates.
- Improves concrete pumpability and finishing quality.
- The dispersion properties of **CHRYSO®Delta CQ 11** allow the user to optimise the cement content when a specified mechanical strength is required.

PACKAGING

- IBC 1000L
- Bulk delivery on request

FIELDS OF APPLICATION

CHRYSO®Delta CQ 11 is recommended for all concrete mixes where low water content, improved cementitious material performance, high workability retention and very high strengths characteristics are desirable.

- All cement types
- Precast elements
- Use of Supplementary Cementitious Materials
- Concrete for highly reinforced structures
- High Performance Concrete
- Ready-mix concrete
- Extended workability retention
- Hot weather concreting
- Plastic or fluid concretes
- Pumped concrete
- Self consolidating concrete
- etc

CHRYSO®Delta CQ 11

New Generation, high range water reducing/
superplasticizing admixture

INDICATIVE INFORMATION

Product Nature	liquid
Color	Pale yellow
Lifetime	12 months
Specific gravity	1,050 ± 0,020
pH	4,50 ± 2,00

Cl⁻ ion content: nil to EN 934 and BS 5075.

METHOD OF USE

0.5 to 2 litres for 100 kg of cement.

- The optimum dosage of this product can only be established after trial tests, taking into account the rheological characteristics and the required mechanical performances of the concrete.
- It can be added: - either within mixing water, or at the end of the mixing cycle (extra mixing time) - or gradually: part in the water before mixing, part during the mixing cycle.
- Should the product be added to fresh concrete, into the mixing truck, it is necessary to mix at high speed, and then at low speed (with a minimum of 3 minutes, at each speed).
- Dosage rates of **CHRYSO®Delta CQ 11** are dependent upon desired concrete performance characteristics and variables including cement quantity and chemistry, concrete temperature and curing conditions.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using outside recommended dosage ranges.

PRECAUTIONS

- Protect from frost.
- Use at a temperature above 0° C.
- Should the product freeze, it will recover its properties. After thawing, an efficient agitation is necessary until the product is entirely homogeneous again.

Compatibility:

- **CHRYSO®Delta CQ 11** is compatible with all types of Portland cement, class C and F fly ash, GGBS, microsilica, fibers and approved air entraining admixtures.
- **CHRYSO®Delta CQ 11** is compatible with other CHRYSO admixtures when used in the same concrete mix, but should be added to the mix separately and must not be mixed together prior to addition.

NORMATIVE AND REGULATORY INFORMATION

- This product conforms to ASTM C 494 Type F and G, and BSEN 934 2

SAFETY

CHRYSO®Delta CQ 11 is not considered dangerous to handle. Prior to any use, please read carefully the Material Safety Data Sheets.