

CHRYSO®Premia CQ 37

High range water reducing Super plasticizing admixture for High Early Strength Concrete



DESCRIPTION

CHRYSO®Premia CQ 37 is a new generation superplasticizer high range water reducer, based on modified polycarboxylate polymers. **CHRYSO®Premia CQ 37** is especially recommended for concrete requiring high early age and long term strengths, while maintaining the workability and superior performances for concrete containing supplementary cementitious materials, such as GGBS, Fly Ash, silica fume.

CHRYSO®Premia CQ 37 enables the production of concrete with very low water-cement ratios.

CHRYSO®Premia CQ 37 can be used in the production of high fines content concrete such as Self Compacting Concrete (SCC), flowable concrete.

BENEFITS

- Dramatically increases early compressive and flexural strengths without detriment to ultimate strengths.
- The dispersion properties of **CHRYSO®Premia CQ 37** allow the user to optimize the cement content when a specified mechanical strength is required.
- Thanks to its short term performances, **CHRYSO®Premia CQ 37** allows either to reduce the time before demoulding or to save energy by decreasing temperature or time of steam curing.

PACKAGING

- IBC 1000L
- Bulk delivery on request

FIELDS OF APPLICATION

CHRYSO®Premia CQ 37 is recommended for all concrete mixes where low water content, improved cementitious material performance (more Mpa/kg), accelerated set times, reduced curing costs and very high early strengths characteristics are desirable.

- All cement types
- Precast
- Use of Supplementary Cementitious Materials
- Concrete for highly reinforced structures
- High Performance Concrete
- Prestressed concrete
- Ready-mix concrete
- High early and ultimate strength
- Plastic or fluid concretes
- Pumped concrete
- Hot weather concreting
- etc

CHRYSO®Premia CQ 37

High range water reducing Super plasticizing admixture for High Early Strength Concrete

INDICATIVE INFORMATION

Product Nature	liquid
Color	Pale yellow
Lifetime	12 months
Specific gravity	1,030 ± 0,020
pH	4,00 ± 2,00

Cl⁻ ion content: nil to EN 934 and BS 5075.

METHOD OF USE

0.3 to 3.0 kg for 100 kg of cement.

- The optimum dosage of this product can only be established after trial tests, taking into account the rheological characteristics and the required mechanical performances of the concrete.
- It can be added: - either within mixing water, or at the end of the mixing cycle (extra mixing time) - or gradually: part in the water before mixing, part during the mixing cycle.
- Should the product be added to fresh concrete, into the mixing truck, it is necessary to mix at high speed, and then at low speed (with a minimum of 3 minutes, at each speed).
- Dosage rates of **CHRYSO®Premia CQ 37** are dependent upon desired concrete performance characteristics and variables including cement quantity and chemistry, concrete temperature and curing conditions.
- Because local job conditions vary, please contact your local CHRYSO sales representative for further assistance if using outside recommended dosage ranges.

PRECAUTIONS

- Protect from frost.
- Use at a temperature above 0° C.
- Should the product freeze, it will recover its properties. After thawing, an efficient agitation is necessary until the product is entirely homogeneous again.

Compatibility:

- **CHRYSO®Premia CQ 37** is compatible with all types of Portland cement, class C and F fly ash, GGBS, microsilica, fibers and approved air entraining admixtures.
- **CHRYSO®Premia CQ 37** is compatible with other CHRYSO admixtures when used in the same concrete mix, but should be added to the mix separately and must not be mixed together prior to addition.

NORMATIVE AND REGULATORY INFORMATION

- This product conforms to ASTM C 494 Type F, and BSEN 934 2

SAFETY

CHRYSO®Premia CQ 37 is not considered dangerous to handle. Prior to any use, please read carefully the Material Safety Data Sheets.